



www.sherwin-williams.com

111.13

**H&C<sup>®</sup>**

# CONCRETE & MASONRY WATERPROOFING SEALER

<u>DESCRIPTION</u>	<u>CHARACTERISTICS</u>	<u>SURFACE PREPARATION</u>																
<p><b>H&amp;C Concrete &amp; Masonry Waterproofing Sealer</b> is a quality acrylic sealer that penetrates and protects bare, aged, dry, and porous surfaces. Because it penetrates, it resists water damage long after the water beading is gone.</p> <p><b>Features:</b></p> <ul style="list-style-type: none"> <li>• a weather resistant moisture barrier</li> <li>• protects concrete, masonry and brick against water-caused deterioration and damage</li> <li>• for interior or exterior application</li> <li>• guards against efflorescence, spalling, repeated freeze-thaw cycles, deicing salts, and general weathering and degradation caused by water infiltration.</li> </ul> <p><b>Recommended Residential Uses:</b></p> <ul style="list-style-type: none"> <li>• interior/exterior</li> <li>• concrete</li> <li>• brick</li> <li>• masonry</li> <li>• cinder block</li> <li>• flagstone</li> <li>• canvas</li> <li>• stucco</li> </ul> <p><b>Not recommended on surfaces subject to vehicle traffic.</b></p> <p><b>For use on BARE surfaces only.</b></p>	<p><b>Color:</b> Clear when dry Milky when wet</p> <p><b>Coverage</b> <b>sq ft/gal</b></p> <table> <tr> <td>Concrete floors</td> <td>200 - 250</td> </tr> <tr> <td>Porous concrete</td> <td>150 - 200</td> </tr> <tr> <td>Concrete block</td> <td>125 - 150</td> </tr> <tr> <td>Brick</td> <td>100 - 150</td> </tr> <tr> <td>Stucco</td> <td>100 - 150</td> </tr> </table> <p>Coverage will vary depending on the porosity and texture of the substrate One coat is usually sufficient.</p> <p><b>Drying Time, @ 77°F, 50% RH:</b> temperature and humidity dependent</p> <table> <tr> <td>Touch:</td> <td>15 minutes</td> </tr> <tr> <td>To recoat</td> <td>within 2 - 4 hours</td> </tr> <tr> <td>Light Foot Traffic:</td> <td>24 hours</td> </tr> </table> <p><b>Flash Point:</b> none</p> <p><b>Finish:</b> Flat</p> <p><b>Vehicle Type:</b> Acrylic</p> <p><b>50.043054 Clear</b></p> <p><b>VOC (less exempt solvents):</b> 114 g/L; 0.95 lb/gal</p> <p><b>Volume Solids:</b> 9 ± 2%</p> <p><b>Weight Solids:</b> 9 ± 2%</p> <p><b>Weight per Gallon:</b> 8.4 lb ± 2%</p>	Concrete floors	200 - 250	Porous concrete	150 - 200	Concrete block	125 - 150	Brick	100 - 150	Stucco	100 - 150	Touch:	15 minutes	To recoat	within 2 - 4 hours	Light Foot Traffic:	24 hours	<p><b>Testing:</b> Due to the wide variety of substrates, preparation methods, application methods and environments, the customer should test the product in an inconspicuous spot for adhesion and compatibility prior to full scale application.</p> <p>All surfaces must be clean, dry and free of grease, oil, paint, sealers, etc. To clean, use H&amp;C Degreaser, following label directions, rinse thoroughly and allow the surface to dry. If mold mildew or fungus are present, kill and remove by cleaning with a solution of 1 part household bleach to 3 parts water.</p> <p><b>Bare Concrete:</b> New concrete must be cured 45 days. All horizontal concrete must be etched with H&amp;C Concrete Etching Solution first, following label directions. For very smooth surfaces (troweled surfaces with no porosity) use H&amp;C Concrete Etching Solution at full strength. For smooth-troweled concrete with some porosity, 1 part H&amp;C Concrete Etching Solution to two parts water should be used. Do not etch painted surfaces. Prepared concrete should have a pH between 6 and 10.</p> <p><b>Repair:</b> For the best waterproofing protection on vertical concrete and masonry, patch and repair cracks and crevices where water can enter. Use ConSeal Sealants and Patches on exterior surfaces following label directions. On floor surfaces, use appropriate patching material. Patching compounds will generally be visible through clear coatings.</p>
Concrete floors	200 - 250																	
Porous concrete	150 - 200																	
Concrete block	125 - 150																	
Brick	100 - 150																	
Stucco	100 - 150																	
Touch:	15 minutes																	
To recoat	within 2 - 4 hours																	
Light Foot Traffic:	24 hours																	

111.13



H&C®

CONCRETE & MASONRY

WATERPROOFING SEALER

**APPLICATION**

- Apply under dry conditions only. Do not apply if rain is expected within 24 hours following application.
- Air and surface temperature should be between 50° and 90°F for 24 hours following application.
- Do not over-apply
- Stir thoroughly before and during application.
- Apply at package consistency on dry to slightly damp surfaces.
- Do not reduce.

**Brush**—Use a nylon/polyester brush

**Roller**—Use a 3/8" - 1/2" nap cover

**Spray—Airless**

Pressure ..... 1500 psi

Tip ..... .011" - .017"

**Spray—Conventional**

Air Pressure ..... 30 - 50 psi

Fluid pressure ..... 15 - 20 psi

Cap/Tip ..... 704/FX or equivalent

**HVLP**

Cap/Needle ..... Titan #3 or equivalent

Backrolling or backbrushing is recommended after spraying.

Apply with a synthetic brush, pad, roller mop, squeegee, or spray. Back brush after spray application. On horizontal surfaces, remove puddles by reworking or wiping up. Do not over apply. One coat is usually adequate. For extremely porous surfaces, apply a second coat within 2 to 4 hours of the first coat working in a second coat thoroughly. A sample brush out on the surface to be treated is recommended to make sure you achieve desired clarity. This will ensure proper penetration and application level. For best results, surface and air temperature should not fall below 50°F for the 24 hour period following application. Dries thoroughly in 24 hours in optimal drying conditions.

**CLEANUP INFORMATION**

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water or a waterless hand cleaner. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using any solvent.

**CAUTIONS**

NOTE: Do not use this product on non-porous surfaces. To determine porosity, splash some water against the surface to be protected. If the water rapidly sinks in and darkens the surface, the surface is porous and needs protection. If the surface does not darken, test again in a few months.

**LABEL CAUTIONS**

Use only with adequate ventilation. To avoid over-exposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, get medical attention immediately. WARNING: This product contains a chemical known to the State of California to cause cancer. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

LCE 4/26/2001 50.043054 02 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.



www.sherwin-williams.com



108.20

# LOXON<sup>®</sup> CONDITIONER A24-100 SERIES

## CHARACTERISTICS

**Loxon Conditioners** are 100% acrylic emulsion conditioners that will penetrate and seal interior and exterior surfaces and bond light chalk to the surface. These sealers allow new concrete, stucco, and other cementitious surfaces to be coated prior to a 30 day cure, and will adhere to new or existing concrete with a pH from 6 to 13.

**Color:** Clear and Guide Coat White

**Coverage:** 200-300 sq ft/gal

**Drying Time, @ 77°F, 50% RH:**

temperature and humidity dependent

Touch: 30 minutes

Tack free: 1 hour

Recoat: 3 hours

**Flash Point:** 201°F, PMCC

**Finish:** 0-10 units @ 85°

**Tinting with Blend-A-Color:**

White up to 1 oz. not controlled

**Vehicle Type:** Acrylic

**A24W100 A24V100**

**VOC:**

grams/liter 106 129

lb/gal 0.88 1.08

**Volume Solids: ± 2%** 19% 14

**Weight Solids: ± 2%** 26% 16

**Weight per Gallon:** 9.1 lb 8.5

## SPECIFICATION

### **Concrete, Stucco, Block**

1 ct. Loxon Conditioner

2 cts. Appropriate architectural topcoat within 7 days

## APPLICATION

Do not build a surface glaze.

Do not apply to a damp surface.

Do not apply over heavy chalk.

Do not apply if the surface temperature is below 50°F, when rain is expected within 3 hours, or when the relative humidity is 90% or more.

No reduction necessary.

### **Brush**

Use a nylon/polyester or foam brush.

### **Roller**

Use a 3/8" to 3/4" nap synthetic cover.

### **Pad**

### **Spray—Airless**

Pressure ..... 700-1000 psi

Tip ..... .015" - .019"

## SURFACE PREPARATION

### **New and Previously Painted**

Remove all surface contamination (peeling paint, heavy chalk, efflorescence, laitance, concrete dust, etc.) by washing or pressure washing with **ProClean™ Prep Wash Concentrated Cleaner** or other appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface.

### **Concrete, Stucco, Block**

Allow new surfaces must cure for at least 7 days. Remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, and form release and curing agents.

### **Mildew**

Remove before painting by washing with **ProClean™ Mildew Eliminator** or a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

### **Priming**

For better performance on masonry, **Loxon Masonry Primer (exterior)** or **PrepRite Masonry Primer (interior)** will provide a hiding coat with excellent film build. Both can be applied to new or existing concrete with a pH of 6 to 13.



# LOXON<sup>®</sup> CONDITIONER

## A24-100 SERIES

### CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. Flush spray equipment after cleaning with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

### LABEL ANALYSIS **A24W100**

Pigment by weight .....	13%
Titanium Dioxide .....	2%
Silica/Silicates .....	11%
Vehicle by weight .....	87%
Acrylic Resin .....	12%
Water .....	72%
Glycol .....	1%
Esters .....	1%
Additives .....	1%
Total .....	100%

### CAUTIONS

For interior and exterior use.  
Protect from freezing.

Loxon Conditioners must be topcoated within 7 days or the surface may need to be recleaned.

**Label Caution**

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH/MSHA TC21C or equivalent). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, get medical attention immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains a chemical known to the State of California to cause cancer. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

LCE 10/29/99  
03 00 A24W100  
01 00 A24V100

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.



# THOROCLEAR® SPECIAL

## Clear reactive silicate water repellent

### Advantages

- Penetrating sealer – Does not alter surface appearance
- Breathable – Allows interior moisture vapor to escape
- Water repellent – Facilitates water runoff
- Water based, VOC compliant – Environmentally friendly

### Where to Use Thoroclear® Special

- Horizontal and vertical
- Concrete
- Aged limestone
- Interior or exterior

### How to Apply Thoroclear® Special

#### Surface Preparation

- 1 All surfaces must be structurally sound, clean, fully cured (28 days), and free of all dust, dirt, bitumens, efflorescence, oil, pollution deposits, all curing, forming, and parting compounds, and all other foreign matter. New stone should age a minimum of 1 year before sealing.
- 2 Complete all caulking, pointing, or restoration work before application and allow to cure. If application must precede such work, carefully avoid application of Thoroclear® Special to joint faces. Contamination may cause sealant adhesion problems.
- 3 For blemish or stainfree results, especially on light colored or white surfaces, surface cleanliness is critical.
- 4 Surface must be dry and free of frost. After rainfall, allow surface to dry 2 to 3 days or longer to avoid a hazing effect.

#### Application

- 1 Apply when surface and air temperatures are above 40°F (4°C) and below 90°F (32°C).
- 2 Apply directly from the container using a good quality brush, roller, or low-pressure sprayer.
- 3 For vertical substrates saturate the surface from the bottom up obtaining a 6 - 12 inch rundown.
- 4 Apply to horizontal surfaces in a uniform manner in sufficient quantity to completely wet out the substrate.
- 5 Care should be taken to treat in one coat prior to drying. Thoroclear® Special will repel itself.

#### Clean Up

Clean all tools and equipment directly after use with soap and water.

### For Best Performance

- Slight darkening might occur on some limestones containing slate or iron; test panels are suggested.
- A test application is recommended to determine coverage rate, water repellence, and appearance.
- Thoroclear® Special is a water-repellent system; where a waterproofing system is required, contact Technical Service for recommendation on other Thoro products.
- Not recommended for application to aluminum plastics, foam insulation, or any EIFS system.
- Certain combinations of aggregates, cements, and manufacturing processes may cause Thoroclear® Special to darken or excessively highlight substrates; darkening or highlighting may particularly be a problem when variations in shading occur in colored concrete. Conduct a test on the actual substrate before applying to entire project.
- Will not inhibit water penetration through unsound or cracked surfaces or areas with defective flashing, caulking, or structural waterproofing.
- Do not not apply during inclement weather, or if rain is expected within 8 hours.
- To prevent damage to nearby shrubbery and landscaping, cover or protect with drop cloth. Also protect incidental glass, metal, and plastic building components, including polystyrene beadboard and fiberglass.
- Do not use on previously painted surfaces.
- Protect from freezing. Frozen material should be placed in a warm spot to thaw. Do not force thawing by direct heat.
- Do not use Thoroclear® Special on brick, freshly quarried stone or slate.
- Make certain the most current version of this data guide is being used; call Customer Service (1-800-433-9517) to verify the most current version .
- Proper application is the responsibility of the user. Field visits by ChemRex Inc. personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job site.

## Order Information

### Packaging

Thoroclear® Special

- 1 gallon (3.8 L) cans
- 5 gallon (19 L) cans
- 30 gallon (114 L) drums
- 55 gallon (208 L) drums

### Coverage

- 200 - 300 sq. ft. per gallon (4.9 - 7.4 m<sup>2</sup>/L), varies with porosity of surface

## Warning

Thoroclear® Special contains potassium methyl silicate and water

### Risks

May be irritating to the eyes and skin. Inhalation of vapors may cause irritation to nose, throat and lungs.

### Precautions

KEEP OUT OF THE REACH OF CHILDREN. Use appropriate personal protective equipment while mixing or handling this product. Avoid contact with skin and eyes. Use splash-proof goggles or other protective eyewear meeting the most current ANSI Z87.1 standards. Use impervious gloves while handling. Use in ventilated area. If poor ventilation exists, use organic vapor or similar type NIOSH approved respirator.

## First Aid

In case of eye or skin contact, flush eyes or exposed area thoroughly with water. If irritation persists call a physician. If swallowed, CALL A PHYSICIAN IMMEDIATELY. Only induce vomiting at the instruction of a physician. NEVER GIVE ANYTHING BY MOUTH TO AN UNCONSCIOUS PERSON. Use in a well ventilated area. Avoid breathing mists and vapors. If needed use a MSHA/NIOSH approved respirator.

## Spills/Storage

Use mild acid solution (acetic acid) to neutralize spills. Clean up spills using sand or other inert materials. Keep spills out of sewers and bodies of water. Material is non-combustible. For further information and handling instructions read the appropriate Thoro System Products Material Safety Data Sheet.

For more information see Material Safety Data Sheet (MSDS) for this product.

## Proposition 65

This product does not knowingly contain chemicals known to the state of California to cause cancer, birth defects or other reproductive harm.

## VOC Content

0 g/L.

**For help in chemical emergencies involving spills, leaks, fire or explosion, call ChemTrec toll free, 1-800-424-9300 day or night.**

**Customer Service:** 1/800/433-9517

**Technical Services:** 1/800/ChemRex (1/800/243-6739)

**Web Site:** [www.chemrex.com](http://www.chemrex.com)

### Limited Warranty Notice

Every reasonable effort is made to apply ChemRex Inc. exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, CHEMREX INC. MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and CHEMREX INC. shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the ChemRex Inc. Technical Manager.



**ChemRex Inc.**

889 Valley Park Drive; Shakopee, MN 55379

**Manufacturing Plants:** Allentown, PA; Bloomington, MN; Bristol, PA; Caguas, PR; Centerville, IN; Denver, CO; Forest Hill, TX; Fort Wayne, IN; Gurnee, IL; Houston, TX; Lancaster, TX; Marietta, GA; Mattawan, MI; Newark, CA; Rancho Cucamonga, CA; Reynolds, GA; Seattle, WA; Streetsboro, OH; Tipp City, OH; Toronto (Canada); Montreal (Canada); Edmonton (Canada)

**Regional Warehouses:** Atlanta, GA; Aurora, OH; Brampton, Ontario (Canada); Chicago, IL; Dallas, TX; Fairfield, NJ; Hayward, CA; Ontario, CA





# THOROSHIELD®

## Clear, water-based urethane protective coating

### Advantages

- Water-based
- Excellent abrasion resistance
- Excellent resistance to ultraviolet rays
- Non-yellowing
- Reduces concrete dusting and staining
- Recoatable
- Easy to apply by brush or roller
- Environmentally friendly

### Where to Use Thoroshield®

- As a sealer over concrete, masonry and painted surfaces
- Vertical and horizontal surfaces
- Interior and exterior use
- Topcoat for Thorocoat® F-74

### How to Apply Thoroshield®

#### Surface Preparation

- 1** Surface to be coated should be thoroughly clean of any dirt, waxes, foreign materials, loosely adhered paints or coatings. Substrate must be thoroughly dry and fully cured 28 days.
- 2** Abrasive shotblasting is the recommended method of surface preparation for smooth and/or dense substrates. Other methods may include most mechanical means such as sandblasting, waterblasting or grinding with specialty equipment. Pre-cleaning by chemical means may be necessary prior to mechanical surface preparation to remove certain types of contaminants such as grease, oil, efflorescence, etc.

#### Mixing

Stir gently for 1 - 3 minutes. Avoid over-agitation. Do not dilute.

#### Application

- 1** Apply Thoroshield® to a clean, dry surface with a soft bristle brush or a 1/4" (6 mm) nap roller. Apply only when surface temperature is above 40°F (4°C). Remove excess material from brush or roller to avoid foamy buildup during application. Spraying this material is not recommended.

- 2** Apply evenly; do not allow puddles or a heavy surface film to develop. One coat is generally adequate for most surfaces. When service conditions require maximum protection, or when coating porous surfaces, two coats are recommended.

- 3** Allow a minimum 2 - 4 hours cure time before applying second coat.

#### Clean Up

Clean immediately with soap and water. Cured material must be removed by mechanical means.

#### For Best Performance

- Make certain the most current version of this data guide is being used; call Customer Service (1-800-433-9517) to verify the most current version .
- Proper application is the responsibility of the user. Field visits by ChemRex Inc. personnel are for the purpose of making technical recommendations only, and are not to supervise or provide quality control on the job site.

#### Technical Data

Abrasion resistance	
Taber abraser (calibrase CS-10, 1,000 gram load, 1,000 revolutions), % weight loss	
	4.27
Flexibility	
	Passed 1/8" (3 mm) mandrel bend

Chemical Resistance	Continuous ponding for 7 days
Gasoline	No effect
Motor oil	No effect
5% NaOH	No effect
5% H <sub>2</sub> SO <sub>4</sub>	Film lifted
50% Liquid detergent	No effect
Hydraulic fluid	No effect

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

## Order Information

### Packaging

- 1 gallon (3.7 L) pails
- 5 gallon (18.9 L) pails
- 30 gallon (113.5 L) drums

### Coverage

One gallon covers approximately 200 sq. ft. (4.9 m<sup>2</sup>/L) depending on the porosity of the surface.

## Danger

Thoroshield™ contains ethylene glycol butyl ether, ethylene glycol, diethylene glycol butyl ether

### Risks

May cause skin, eye and respiratory irritation. Ingestion may cause irritation. Reports associate repeated or prolonged occupational overexposure to solvents with permanent brain, nervous system, liver and kidney damage. Repeated ingestion may cause kidney damage. May be absorbed through skin. Repeated or prolonged exposure increases the risk of absorption. INTENTIONAL MISUSE BY DELIBERATELY INHALING THE CONTENTS MAY BE HARMFUL OR FATAL.

### Precautions

KEEP OUT OF THE REACH OF CHILDREN. Keep container closed. Use only with adequate ventilation. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling. Avoid breathing vapors. DO NOT take internally. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations.

## First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. SEEK IMMEDIATE MEDICAL ATTENTION.

In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION.

Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs, or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

## Proposition 65

This product contains materials listed by the state of California as known to cause cancer, birth defects or other reproductive harm.

## VOC Content

458 g/L or 3.85 lbs./gal. less water and exempt solvents.

*For medical emergencies only, call ChemTrec (1/800/424-9300)*

**Customer Service:** 1/800/433-9517

**Technical Services:** 1/800/ChemRex (1/800/243-6739)

**Web Site:** [www.chemrex.com](http://www.chemrex.com)

### Limited Warranty Notice

Every reasonable effort is made to apply ChemRex Inc. exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, CHEMREX INC. MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and CHEMREX INC. shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the ChemRex Inc. Technical Manager.



**ChemRex Inc.**

889 Valley Park Drive; Shakopee, MN 55379

**Manufacturing Plants:** Allentown, PA; Bloomington, MN; Bristol, PA; Caguas, PR; Centerville, IN; Denver, CO; Forest Hill, TX; Fort Wayne, IN; Gurnee, IL; Houston, TX; Lancaster, TX; Marietta, GA; Mattawan, MI; Newark, CA; Rancho Cucamonga, CA; Reynolds, GA; Seattle, WA; Streetsboro, OH; Tipp City, OH; Toronto (Canada); Montreal (Canada); Edmonton (Canada)

**Regional Warehouses:** Atlanta, GA; Aurora, OH; Brampton, Ontario (Canada); Chicago, IL; Dallas, TX; Fairfield, NJ; Hayward, CA; Ontario, CA

